

No. 2141591

TO SUGAWA IONWOOD SDN BHD

Test Results Report

(Far infrared radiation measurement test)

28-Jul 2014

特定非営利活動法人(NPO)



日本機能性イオン協会
JAPAN ASSOCIATION OF ION RESEARCH AND APPLICATION

Ohshiro Building 5F, Higashinakajima 1-19-11,
Higashiyodogawa-ku Osaka-city, Osaka 533-0033, Japan
Phone/Fax:+81-6-4809-4098/+81-6-4809-4099

No.2141591

July 28, 2014

To SUGAWA IONWOOD SDN BHD

Test Results Report

(Far infrared radiation measurement test)

Japan Association of Ion Research and Application(JAIRA)

Chairman Toshikatsu Asada

Ohshiro Building 5F, Higashinakajima 1-19-11,

Higashiyodogawa-ku Osaka-city, Osaka 538-0033, Japan

Phone/Fax:+81-6-4809-4098/+81-6-4809-4099

Sample ION WOOD

Measurement instrument NIHON DENSHI Co.,LTD. JL-500


Measurement temperature 25°C

Result

Sample	Average Emissivity (%)
ION WOOD	88.93


End of description

ION WOOD, (25°C)



RESOL : 32cm-1
TEMP : 25
AMPGAIN : x32
P.INT : 16cm-1
SCANS : 200
S.SPEED : MCT
S.NUMBER: 99
M.DATE : 7/24/14

ION WOOD, (25'C)



RESOL : 32cm-1
TEMP : 25
AMPGAIN : x32
P. INT : 16cm-1
SCANS : 200
S. SPEED : MCT
S. NUMBER: 99
M. DATE : 7/24/14